


# Chemical resistance guide

<b>LEVEL 0</b>	<b>LEVEL 1</b>	<b>LEVEL 2</b>	<b>LEVEL 3</b>	<b>LEVEL 4</b>	<b>LEVEL 5</b>	<b>LEVEL 6</b>
< 10 min	10 > 29 min	30 > 59 min	60 > 119 min	120 > 239 min	240 > 479 min	> 480 min

## duoSHIELD™ PFT Nitrile 240



- Length: 240 mm/ 9.4"
- Palm thickness: 0.08 mm/ 3.1 mil
- Chemical performance: Type B
- Biological risk: AQL 0.65 / Level 3
- Particles level: N/A / N/A
- Virus resistant
- Allergies: Contains Latex protein / Free of Thiazoles and Thiurams / Powder-free
- Design: Ambidextrous / Powder-free
- Colour: Blue
- Mechanical risk: N/A
- Applications: Laboratory / General workplace / Healthcare

64-19-7 Acetic acid 99%	<b>LEVEL 0</b> 4 min
67-68-5 Dimethyl sulfoxide 99% (DMSO)	<b>LEVEL 0</b> 8 min
64-17-5 Ethanol 99.8%	<b>LEVEL 1</b> 11 min
1239-45-8 Ethidium bromide 5%	<b>LEVEL 6</b> 480 min
50-00-0 Formaldehyde 37%	<b>LEVEL 6</b> 480 min DR -40%
7647-01-0 Hydrochloric acid 37%	<b>LEVEL 3</b> 102 min
7722-84-1 Hydrogen peroxide 30%	<b>LEVEL 6</b> 480 min DR -6%

7697-37-2  
Nitric acid 65%

**LEVEL 0**  
**3 min**

1310-73-2  
Sodium hydroxide 40%

**LEVEL 6**  
**480 min**  
**DR -11%**

7664-93-9  
Sulphuric Acid 50%

**LEVEL 6**  
**480 min**

DISCLAIMER: The data provided was based on gloves tested under laboratory conditions, in accordance with EN 16523-1:2015 (formerly EN 374-3:2003) and EN 374-4:2013. The information is for guidance only and may not reflect the user's application. A risk assessment should always be made by purchaser to assess the suitability of gloves for a specific application.

**Biozym**  
SCIENCE IS OUR BUSINESS  
[www.biozym.com](http://www.biozym.com)

**Biozym Scientific GmbH**  
Tel.: +49 (0) 5152 9020  
Mail: [support@biozym.com](mailto:support@biozym.com)

**Biozym Biotech Trading GmbH**  
Tel.: +43 (0) 1 334 0156 0  
Mail: [support@biozym.com](mailto:support@biozym.com)



[www.shieldscientific.com](http://www.shieldscientific.com)

Contact: [info@shieldscientific.com](mailto:info@shieldscientific.com)

© 2026- Copyright protected SHIELD Scientific - All rights reserved - Printed : 16/02/2026