

# Chemical resistance guide

<b>LEVEL 0</b>	<b>LEVEL 1</b>	<b>LEVEL 2</b>	<b>LEVEL 3</b>	<b>LEVEL 4</b>	<b>LEVEL 5</b>	<b>LEVEL 6</b>
< 10 min	10 > 29 min	30 > 59 min	60 > 119 min	120 > 239 min	240 > 479 min	> 480 min

## ecoSHIELD™ Eco Latex PF 250



- Length: 250 mm/ 9.8"
- Palm thickness: 0.16 mm/ 6.3 mil
- Chemical performance: Type B / High chemical splash protection
- Biological risk: AQL 0.65 / Level 3
- Particles level: N/A / N/A
- Virus resistant
- Allergies: Latex protein < 50 µg/g / Free of Thiazoles and Thiurams / Powder-free
- Design: Ambidextrous / Powder-free
- Colour: Natural colour
- Mechanical risk: N/A
- Applications: Laboratory / General workplace / Healthcare
- Chlorination: Double

64-19-7 Acetic acid 99%	<b>LEVEL 0</b> 3 min
67-64-1 Acetone 99.8%	<b>LEVEL 0</b> 1 min
75-05-8 Acetonitrile 99.9%	<b>LEVEL 0</b> 2 min
79-06-1 Acrylamide 40%	<b>LEVEL 6</b> 480 min
107-13-1 Acrylonitrile 99%	<b>LEVEL 0</b> 1 min
1336-21-6 Ammonium hydroxide 25%	<b>LEVEL 0</b> 7 min
75-09-2 Dichloromethane 99%	<b>LEVEL 0</b> 0 min

64-17-5 Ethanol 70%	LEVEL 0 9 min
1239-45-8 Ethidium bromide 5%	LEVEL 6 480 min
50-00-0 Formaldehyde 37%	LEVEL 6 480 min DR -77%
7647-01-0 Hydrochloric acid 37%	LEVEL 2 57 min
7722-84-1 Hydrogen peroxide 30%	LEVEL 6 480 min DR -26%
67-63-0 Isopropanol 70%	LEVEL 1 11 min
67-56-1 Methanol 99.9%	LEVEL 0 0 min
80-62-6 Methyl Methacrylate 99%	LEVEL 0 0 min
1310-73-2 Sodium hydroxide 40%	LEVEL 6 480 min DR -60%
1310-73-2 Sodium Hydroxide 50%	LEVEL 6 480 min
7681-52-9 Sodium Hypochlorite 13%	LEVEL 6 480 min
7664-93-9 Sulphuric Acid 95%-98%	LEVEL 1 18 min
7664-93-9 Sulphuric Acid 50%	LEVEL 6 480 min
1330-20-7 Xylene 98.5%	LEVEL 0 1 min

DISCLAIMER: The data provided was based on gloves tested under laboratory conditions, in accordance with EN 16523-1:2015 (formerly EN 374-3:2003) and EN 374-4:2013. The information is for guidance only and may not reflect the user's application. A risk assessment should always be made by purchaser to assess the suitability of gloves for a specific application.



**Biozym Scientific GmbH**  
Tel.: +49 (0) 5152 9020  
Mail: support@biozym.com

**Biozym Biotech Trading GmbH**  
Tel.: +43 (0) 1 334 0156 0  
Mail: support@biozym.com



Biozym Scientific



biozym\_scientific



Biozym Scientific



Newsletter

[www.shieldscientific.com](http://www.shieldscientific.com)

Contact: [info@shieldscientific.com](mailto:info@shieldscientific.com)

© 2026- Copyright protected SHIELD Scientific - All rights reserved - Printed : 16/02/2026