



Chemical resistance guide

LEVEL 0	LEVEL 1	LEVEL 2	LEVEL 3	LEVEL 4	LEVEL 5	LEVEL 6
< 10 min	10 > 30 min	30 > 60 min	60 > 120 min	120 > 240 min	240 > 480 min	> 480 min

ecoSHIELD* Eco Latex PF 250



- Virus resistant
- Length: 250 mm/ 9.8"
- Palm thickness: 0.16 mm/ 6.3 mil
- Color: #008e30
- Design: Ambidextrous / Powder-free
- Allergies: Latex protein < 50 µg/g / Free of Thiazoles and Thiurams / Powder-free
- Chemical performance: Type B / High chemical splash protection
- Biological risk:
- Mechanical risk: N/A
- Chlorination: Double
- Particles level: N/A / N/A
- Applications: Laboratory / General workplace / Healthcare

64-19-7 Acetic acid 99%	LEVEL 0 3 min
67-64-1 Acetone 99.8%	LEVEL 0 1 min
75-05-8 Acetonitrile 99.9%	LEVEL 0 2 min
79-06-1 Acrylamide 40%	LEVEL 6 480 min
107-13-1 Acrylonitrile 99%	LEVEL 0 1 min
1336-21-6 Ammonium hydroxide 25%	LEVEL 0 7 min
75-09-2 Dichloromethane 99%	LEVEL 0 0 min

64-17-5 Ethanol 70%	LEVEL 0 9 min
1239-45-8 Ethidium bromide 5%	LEVEL 6 480 min
50-00-0 Formaldehyde 37%	LEVEL 6 480 min DR -12%
7647-01-0 Hydrochloric acid 37%	LEVEL 2 57 min
7722-84-1 Hydrogen peroxide 30%	LEVEL 6 480 min DR -38%
67-63-0 Isopropanol 70%	LEVEL 1 11 min
67-56-1 Methanol 99.9%	LEVEL 0 0 min
80-62-6 Methyl Methacrylate 99%	LEVEL 0 0 min
1310-73-2 Sodium Hydroxide 40%	LEVEL 6 480 min DR -16%
1310-73-2 Sodium Hydroxide 50%	LEVEL 6 480 min
7681-52-9 Sodium Hypochlorite 13%	LEVEL 6 480 min
7664-93-9 Sulphuric Acid 95%-98%	LEVEL 1 18 min
7664-93-9 Sulphuric Acid 50%	LEVEL 6 480 min
1330-20-7 Xylene 98.5%	LEVEL 0 1 min

DISCLAIMER: The data provided was based on gloves tested under laboratory conditions, in accordance with EN 16523-1:2015 (formerly EN 374-3:2003) and EN 374-4:2013. The information is for guidance only and may not reflect the user's application. A risk assessment should always be made by purchaser to assess the suitability of gloves for a specific application.